

Technical Specifications for

Nedia S300

Nedia S300 is a 100% straw matrix stitch bonded with photodegradable polypropylene top netting.

Index Value Properties:

Property	Test Method	Typical Value	
		English Units	Metric Units
Material composition	n/a	100% Straw	
Mass per unit area	ASTM D 6475	8.5 oz/sq.yd	288.2 oz/sq.m
Thickness	ASTM D 6525	0.32 inches	8.1 mm
Tensile Strength (MD x TD)	ASTM D 6818	121 x 79 lb/ft.	1.8 x 1.2 kN/m
Elongation (MD x TD)	ASTM D 6818	30% x 35%	
Light Penetration	ASTM D 6567	8%	
Water Absorption	ASTM D 1117	360%	
Manning's N	Observed	0.025	

Channel Performance Design Values*:

Property	Test Method	Typical Value	
		English Units	Metric Units
Unvegetated Shear Stress	ASTM D 6460	1.5 lb/sq. ft	72 Pa
Unvegetated Velocity	ASTM D 6460	6.8 ft./s	2.0 m/s
Vegetated Shear Stress	n/a	n/a	
Vegetated Velocity	n/a	n/a	

* Large scale results obtained by 3rd party GAI Accredited independent laboratory.

Standard Roll Sizes: 8' x 112.5' (2.44m x 34.3m) – 100 sy /roll



www.nedia.com



info@nedia.com

The above information is to the best of our knowledge accurate, but it is not intended to be considered a guarantee. Any implied warranty for a particular use or purpose is excluded. Nedia Enterprises, Inc. will not be liable for any type of damage or losses, directly or indirectly for failure of this product. All test results and properties were obtained from independent laboratory testing. If the product does not meet the above properties, and if a written notice is given to Nedia Enterprises, Inc., within seven days of delivery date, the product will be replaced or refunded.