



Technical Specifications for

**Nedia C400**

Nedia C400 is a 100% coconut fiber matrix stitch bonded between two heavyweight photodegradable top and bottom nettings.

**Index Value Properties:**

Property	Test Method	Typical Value	
		English Units	Metric Units
Material composition	n/a	100% Coconut Fiber	
Mass per unit area	ASTM D 6475	9.5 oz/sq.yd	322 gms/sq.m
Thickness	ASTM D 6525	0.30 inches	7.6 mm
Tensile Strength (MD x TD)	ASTM D 6818	310 x 250 lb/ft.	4.5 x 3.6 kN/m
Elongation (MD x TD)	ASTM D 6818	20 % x 20 %	
Light Penetration	ASTM D 6567	16%	
Water Absorption	ASTM D 1117	399%	
Manning's N	Observed	0.025	

**Channel Performance Design Values\*:**

Property	Test Method	Typical Value	
		English Units	Metric Units
Unvegetated Shear Stress	ASTM D 6460	3.30 lb/sq. ft	158 Pa
Unvegetated Velocity	ASTM D 6460	10.0 ft./s	3.0 m/s
Vegetated Shear Stress	n/a	n/a	
Vegetated Velocity	n/a	n/a	

\* Large scale results obtained by 3<sup>rd</sup> party GAI Accredited independent laboratory.

**Standard Roll Sizes: 8' x 112.5' (2.44m x 34.3m) – 100 sy /roll**



[www.nedia.com](http://www.nedia.com)



[info@nedia.com](mailto:info@nedia.com)

The above information is to the best of our knowledge accurate, but it is not intended to be considered a guarantee. Any implied warranty for a particular use or purpose is excluded. Nedia Enterprises, Inc. will not be liable for any type of damage or losses, directly or indirectly for failure of this product. All test results and properties were obtained from independent laboratory testing. If the product does not meet the above properties, and if a written notice is given to Nedia Enterprises, Inc., within seven days of delivery date, the product will be replaced or refunded.